



RIGID PHENOLIC INSULATION

PROPERTIES	STANDARD	UNITS
NOMINAL DENSITY	EN 1602	40 kg/m ³ +/- 2
THERMAL CONDUCTIVITY	EN 12667	0.021 W/m.K +/- 0.002
TEMPERATURE LIMITS		-180°C to +120°C
SPECIFIC HEAT		1.88 kl/kg. C
COMPRESSIVE STRENGTH	EN 826	
- Parallel to rise		180 kPa +/- 40
- Perpendicular to rise		140 kPa +/- 40
TENSILE STRENGTH	EN 1607	
- Parallel to rise		200 kPa +/- 40
- Perpendicular to rise		180 kPa +/- 40
CLOSED CELL CONTENT	EN ISO 4590	Minimum 95%
Fire Test Classifications		
<ul style="list-style-type: none"> • EN 13501-1 : 2007+A1 : 2009, EuroClass SBI B, S1, D0 • BS476 Part 6 and Part 7 - Results conform to Class O of the UK Building Regulations • Epiradiateur - M1 • ASTM E84 25/50 Flame and Smoke - up to 3 inches thick • NEN 6065/6066 - Klasse 1/2 • DIN 4102 - B1 		
Other information		
<p>This information is furnished without warranty, expressed or implied, except that it is accurate to the best knowledge of Resolco International BV. The data on this sheet relates only to the specific material designated herein. Resolco International BV assumes no legal responsibility for use or reliance upon this data. For information regarding specific applications of the product please contact Resolco International BV.</p>		



Resolco International BV
 Distributieweg 4d
 4906 AD Oosterhout
 Postbus 4203
 4900 CE Oosterhout
 Netherlands



Tel: +31 -(0)162-492444
 Fax: +31-(0)162-492441
 e-mail: info@resolco.com